



Thermal Transfer Polyester Label Material

7810 • 7813

Technical Data

May 2017

Product Description 3M™ Thermal Transfer Polyester Label Materials 7810 and 7813 are durable matte polyester materials that offer high abrasion and chemical resistance. These materials utilize 3M™ Acrylic Adhesive 300, which has excellent quick tack and also bonds well to a variety of surfaces including LSE plastics.

Construction

Product	Facestock	Adhesive	Liner
3M™ Label Material 7810	.0023 in. White Polyester Matte TT TC	300 Acrylic 0.8 mil / 3.2 mils	55# Densified Kraft
3M™ Label Material 7813	.0033 in. Silver Polyester Matte TT TC	300 Acrylic 0.8 mil / 3.2 mils	55# Densified Kraft

(Calipers are nominal values.)

Features

- Matte topcoat provides the advantages of matte coating combined with a surface that is smooth enough for thermal transfer printing. Resin ribbons are recommended for optimum durability. The matte coating resists degradation from scuffing, chemicals, moisture, and wide temperature fluctuations. The topcoat also provides improved ink anchorage for traditional forms of press printing.
- Adhesive bonds well to a wide variety of substrates including metals, high surface energy (HSE) plastics and low surface energy (LSE) plastics. It is ideal for applications requiring high initial adhesion especially to LSE plastic surfaces.
- 55# densified kraft liner assures consistent die cutting.
- UL recognized (File MH16411) and CSA accepted (File 99316).

Application Ideas

- Barcode labels and rating plates
- Property identification and asset labeling
- Warning, instruction, and service labels for durable goods
- Nameplates and durable goods

3M™ Thermal Transfer Polyester Label Material

7810 • 7813

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Adhesive Coat Weight	1.05 to 1.21 g/100 in. ²	3M Method E10MFP01
Release Range	10 to 60 g/2 in.	TLMI Method, 180° removal, 300 in./min.
Service Temperature	-40°F to 300°F (-40°C to 149°C)	
Minimum Application Temperature	50°F (10°C)	
Convertability	Due to the quick flowing aggressive nature of 3M™ Acrylic Adhesive 300, care should be taken during processing. Refer to die cutting/converting section of data page for additional information or the “Guide to Converting and Handling Label Products” technical bulletin for additional information.	

Typical Peel Adhesion Properties

Adhesion: 180° peel test procedure is ASTM D 3330
90° peel test procedure is ASTM D 3330 modified for the angle change

	Initial (10 Minute Dwell/RT)				Conditioned for 3 Days at Room Temperature 72°F (22°C)			
	180° Peel		90° Peel		180° Peel		90° Peel	
Surface	Oz./In.	N/100 mm	Oz./In.	N/100 mm	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	56	61	42	46	67	73	46	50
Polycarbonate	59	67	44	48	61	67	46	50
Polypropylene	53	58	38	42	56	61	38	42
Glass	60	66	42	46	71	78	48	52
HD Polyethylene	35	38	28	31	40	44	28	31
LD Polyethylene	32	35	25	27	42	46	34	37

	Conditioned for 3 Days at 120F (49°C)				Conditioned for 24 hours at 90°F (32°C) at 90% Relative Humidity			
	180° Peel		90° Peel		180° Peel		90° Peel	
Surface	Oz./In.	N/100 mm	Oz./In.	N/100 mm	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	70	77	50	55	68	74	53	58
Polycarbonate	30	33	17	19	55	60	36	39
Polypropylene	54	59	42	46	66	72	44	48
Glass	70	77	50	55	67	73	44	48
HD Polyethylene	40	44	29	32	45	49	32	35
LD Polyethylene	9	10	10	11	36	39	30	33

3M™ Thermal Transfer Polyester Label Material

7810 • 7813

Environmental Performance

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

The properties defined are based on four hour immersions at room temperature (72°F/22°C) unless otherwise noted. Samples were applied to stainless steel panels 24 hours prior to immersion and were evaluated one hour after removal from the solution for peel adhesion. Adhesion measured at 180° peel angle (ASTM D 3330) at 12 inches/minute.

Chemical Resistance:

Chemical	Adhesion to Stainless Steel		Appearance	Edge Penetration
	Oz./in.	N/100 mm	Visual	Millimeters
Isopropyl Alcohol	60	66	No change	0.8
Detergent 1% Alconox® Cleaner	64	70	No change	0
Engine Oil (10W30) @ 250°F (121°C)	64	70	No change	1
Water for 48 hours	66	72	No change	0
pH 4	65	71	No change	0
pH 10	64	70	No change	0
Formula 409® Cleaner	64	70	No change	0
Toluene	33	36	No change	6.5
Acetone	47	51	No change	4.3
Brake Fluid	74	81	No change	0
Gasoline	36	39	No change	5.8
Diesel Fuel	62	68	No change	1
Mineral Spirits	54	59	No change	2.4
Hydraulic Fluid	66	72	No change	0

Temperature Resistance:

300°F (149°C) for 24 hours: no significant visual change

-40°F (-40°C) for 10 days: no significant visual change

Humidity Resistance:

24 hours at 100°F (38°C) and 100% relative humidity: no significant change in appearance or adhesion

Accelerated Aging:

ASTM D 3611: 96 hours at 150°F (65°C) and 80% relative humidity

180° Liner Release, 90 inches/minute: 16 gm./in. width (0.62 N/100 mm)

180° Peel Adhesion from Stainless Steel, 12 inches/minute: 54 oz./in. width (59 N/100 mm)

3M™ Thermal Transfer Polyester Label Material

7810 • 7813

Application Techniques	For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.* For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 50°F (10°C), can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure. *When using solvents, read and follow the manufacturer's precautions and directions for use.
Printing	Facestock is topcoated for improved ink receptivity and is designed for thermal transfer printing. It is printable by all standard roll processing methods. <u>UL Recognized thermal transfer ribbons</u> Advent: 301 Black; 303 Black; 501 Black; 501 Red; 501 Blue; 501 Green Aarmor: AXR-7; AXR-7+; AXR-600 Astromed: R5 CP: 5440 Red; 5640 Blue; 5940 Black Dasco: DR-74; DR-84 Great Ribbon: SDR ICS: ICS-CC-4099.1; ICS-CC-2000 Iimak: SP-330; PrimeMark; SH-36 Intermec: 051864-3; 053258-2; 054048-4; 054195-2 Japan Pulp and Paper: JP Resin 1; JP Resin 2 Blue; JP Resin 2 Red (suitable for indoor use only); JP Resin 2 Green (suitable for indoor use only) Kurz: K501 Markem: 716 (suitable for indoor use only) Mid City Columbia: CGL-80; CGL-80HE NCR: Matrix Resin; Matrix (suitable for indoor use only); PaceSetter; Promark II; Ultra V Pelikan: T016 Ricoh: B110A; B110C; B110CS Sato: Premier 1 Sony: 4050; 4051; 4070; 4072; 4075; 4085; 5070; TR6070; TR6075; Signature Series Resin; Signature Series Wax UBI: HR03; HR04 Zebra: 5095; 5097; 5099; 5100; 5175; 5555
Die Cutting / Converting	Rotary die cutting is recommended. Fanfolding of labels is not recommended. Small labels should be evaluated carefully. Winding tensions should be kept at a minimum to help prevent the adhesive from oozing.

3M™ Thermal Transfer Polyester Label Material

7810 • 7813

Packaging	Finished labels should be stored in plastic bags.
Storage	Store at room temperature conditions of 72°F (22°C) and 50% relative humidity.
Shelf Life	If stored under proper conditions, product retains its performance and properties for two years from date of manufacture.
Technical Information	The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.
Product Selection and Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.
Warranty, Limited Remedy and Disclaimer	Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.
Limitation of Liability	Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

ISO 9001

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.



Industrial Adhesives and Tapes Division
Converter Markets
3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-362-3550
3M.com/converter



3M is a trademark of 3M Company.
Alconox is a registered trademark of Alconox, Inc.
Formula 409 Cleaner is a registered trademark of
Clorox, Inc.
©3M 2017 E 70-0709-1027-1 (5/17)